(12)

## **EUROPEAN PATENT APPLICATION**

- (88) Date of publication A3: 18.03.1998 Bulletin 1998/12
- (43) Date of publication A2: 12.03.1997 Bulletin 1997/11
- (21) Application number: 96306232.8
- (22) Date of filing: 28.08.1996
- (84) Designated Contracting States: DE ES FR GB IT SE
- (30) Priority: 29.08.1995 US 521111
- (71) Applicant: JOHNSON & JOHNSON
  PROFESSIONAL Inc.
  Raynham, Massachusetts 02767-0350 (US)
- (72) Inventors:
  - Caldarise, Salvatore Hanson, Massachusetts 02341 (US)

(51) Int Cl.<sup>6</sup>: **A61F 2/30**, B29C 67/00, B22C 7/02

- Besemer, John W.
   Sudbury, Massachusetts 01776 (US)
- Ritchie, Allan
   New Milton, Hampshire, BH25 5SD (GB)
- Foley, Freank R.
   Byfleet, Surrey, KT14 7AL (GB)
- (74) Representative: Fisher, Adrian John et al CARPMAELS & RANSFORD
   43 Bloomsbury Square London WC1A 2RA (GB)

## (54) Bone prosthesis with protected coating for penetrating bone intergrowth

A bone prosthesis (10) has a growth enhancement coating (C) recessed (30) in and protected by its surface topography. The topographic features define gaps under a few millimeters which are readily spanned by new bone growth, while the features protect the coating (C) from abrasion or physical damage. The topographic features substantially surround the coated regions, and prevent migration of flakes spalled during implantation or microparticles shed by the coating (C) as it is resorbed or incorporated in new bone (50) over time. In a preferred embodiment, edge features cast in the surface (S) of a metal prosthesis (10) include dovetail, undercut or skewed faces (W) which firmly interlock with newly-growing bone (50) to form a strong and shearfree, substantially rigid attachment. The prosthesis (10) may be cast in a mold having a complex surface interlock texture, and these molds may be mass produced by an iterative three-dimensional printing technique to build each mold up in layers in the form of a suitable casting negative. The prosthesis (10) is then cast of molten metal in the mold, and the mold material is broken away and cleaned off, e.g., by an etch. A growth enhancer such as hydroxyapatite (HA) is plasma-sprayed to selectively deposit on and completely cover the floors (f) of the recesses (30) formed in the casting. Preferably, the upper surfaces (S) about the recesses (30) are polished, and the recess walls (W) are overhung so they are masked from the coating process, further than causing the HA coating (C) to adhere only in the protected

floor (f) regions. The HA floors (f) are at the bottom of pits or macropores, at a depth (d) of under three millimeters, and preferably one-half to two millimeters, so that new bone (50) growth spans the gaps and penetrates into the prosthesis (10) over an extended surface textured region (28).




FIG. I

EP 0 761 182 A3



## **EUROPEAN SEARCH REPORT**

Application Number

EP 96 30 6232

	DOCUMENTS CONSIDERED TO BE RELEVAL  Citation of occurrent with indication, where appropriate	Relevant	CLASSIFICATION OF THE
Category	of relevant passages	to claim	APPLICATION (Int.Cl.6)
X	DE 42 11 343 A (S + G IMPLANTS)	1-5.10. 12-16	A61F2/30 B29C67/00
	* the whole document *	ļ	B22C7/02
Α	EP O 399 163 A (ESKA MEDICAL LÜBECK MEDIZINTECHNIK) * the whole document *	1,10,12, 13,15	
A	US 4 179 485 A (TRITTEN)	1,4.10. 12-16	
	* column 3, line 24 - line 30; figure 1	*	   
A	WO 92 21302 A (LUCOCER) * figure 5 *	4,5.16	
A	US 4 795 472 A (CROWNINSHIELD)		
Α	WC 86 C2824 A (LUNDGREN)		
D,A	EP 0 668 062 A (JOHNSON & JOHNSON PROFESSIONAL)		TECHNICAL FIELDS SEARCHED (Int.Cl.6)
D,A	US 5 204 055 A (SACHS)		A61F
i			
ĺ			
	The present search report has been drawn up for all claims		
	Place of search Care of completing of the seed		Examine:
	THE HAGUE 8 January 1998		in, C
	El earner pate	and ple underlying the in let document, but aublis	
Y partic	nent of the same category £ 1 document of	ng date died in the application died for other reasons	
C : non-	otogical backgreend & member of written disclosure & member of editate abcurrient écorument corument	the same patent lamily.	corresponding